

Abstract of the Disclosure

An aluminum alloy extrusion product having improved strength and fracture toughness, the aluminum base alloy comprised of 1.95 to 2.5 wt.% Cu, 1.9 to 2.5 wt.% Mg, 8.2 to 10 wt.% Zn, 0.05 to 0.25 wt.% Zr, max. 0.15 wt.% Si, max. 0.15 wt.% Fe, max. 0.1 wt.% Mn, the remainder aluminum and incidental elements and impurities.